



- The flooring shall be Polyflor Bevel Line PUR, as supplied by Polyflor Ltd. of Manchester, England.
- The flooring shall be flexible PVC tile and plank flooring in 2.5mm thickness.
- It shall have the following laminated construction: circa 0.7mm clear PVC wear layer, circa 0.07mm print film layer, and circa 1.73mm backing ply.
- The flooring shall feature a high quality, cross-linked polyurethane reinforcement to provide superior cleaning benefits, life cycle maintenance savings and optimum appearance retention.



- In accordance with EN 649/EN ISO 10582, the in-use classification must be at least 23/34/43 as described in EN 685/EN ISO 10874: i.e. domestic areas with heavy use; commercial areas with intensive use; and light industrial areas.
- In respect of flame spread, the flooring shall have been fully tested to EN 13501-1 and certified as having Class Bfl-S1, achieving the criteria EN ISO 9239-1 ≥ 8kw/m² and the mandatory requirement of EN ISO 11925-2 pass.
- The flooring shall have been fully tested to ASTM E648 by an independent test house and classified as Class 1 rating, making it suitable for use in institutional, commercial and public buildings.
- The product is classed as DS (dry slip) when tested to EN 13983. It also achieves an R10 rating when tested to DIN 51130 and AS/NZS 4586. For safety flooring with sustainable wet slip resistance, refer to Expona Control or the Polysafe ranges.
- The product's weight should not be more than 4290g/m².
- In respect of light fastness, the flooring shall have been fully tested to ISO 105-B02 Method 3 as having a pass to ≥ 6.



- The flooring will achieve a BRE Global Environmental A+ rating ENP 429 in the Green Guide to Specification.
- The manufacturer should provide a facility to take back and recycle waste vinyl flooring material through the Recofloor scheme.
- Bevel Line achieves a very low VOC emissions result when tested to AgBB standards, is certified by Eurofins as achieving Indoor Air Comfort Gold and is also a FloorScore certified product.



- The manufacturer of the floorcovering must be in possession of a valid quality systems certificate, showing compliance with BS EN ISO 9001.
- The manufacturer of the floorcovering must be in possession of a valid environmental certificate, showing compliance with ISO 14001.



- A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be carried out using a hygrometer, in accordance with the instructions in BS 8203. The result should not exceed 75%RH, once equilibrium has been achieved.
 - The adhesive used must be approved by Polyflor, to ensure full product compatibility.
 - Products must be fully conditioned to the environment in which they are to be installed. See Polyflor installation instructions for details.
 - Installation must be carried out in accordance with BS 8203 and the instructions of Polyflor.
 - Suitable for use with underfloor heating up to 27°C. See Polyflor installation instructions for details.
- NOTE:** The subtle blending of shades and graining variation can best be obtained by the random shuffling of 3-4 packs of tiles.



- Polyflor Bevel Line PUR is suitable for heavy commercial use in corridors, shops, department stores, classrooms, lecture theatres, multi-purpose halls, open-plan offices and other areas with heavy traffic. Polyflor Bevel Line PUR may also be used in heavy light industrial applications, where work is sedentary with occasional use of light vehicles.
- Polyflor Bevel Line PUR is also ideal for use in the home in living rooms, kitchens, bathrooms, entrance halls and conservatories. On-floor temperatures in conservatories can become quite high. It is strongly advised that, in such situations, a Polyflor recommended high temperature adhesive is used. We recommend that adequate UV protection be taken against products being installed in direct sunlight as fading may occur.
- For further information and advice on specific applications, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com.




- At the date of issue the data presented is correct. However, Polyflor Ltd. reserve the right to make changes which do not adversely affect performance or quality.

BEVELline™
THE WOOD & STONE COLLECTION



**PRODUCT
SPECIFICATION**



POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK
 UK SALES DIRECT: +44 (0)161 767 1122 UK SAMPLE REQUESTS: +44 (0)161 767 2551
 EXPORT SALES DIRECT: +44 (0)161 767 1913 TECHNICAL SUPPORT: +44 (0)161 767 1912
 RECEPTION: +44 (0)161 767 1111 UK FAX: +44 (0)161 767 1128
 EXPORT FAX: +44 (0)161 767 1166 E-MAIL: INFO@POLYFLOR.COM
 WEBSITE: WWW.POLYFLOR.COM

James Hallett™
FLOORING



2011

POLYFLOR™
COVERING THE WORLD